

1/1

| Sample No. | Penetration (15 min.) | Percent Asota PP | Percent FSI PP | Percent Std. PP | Percent Modacrylic | Percent Acrylic | Comments |
|------------|-----------------------|------------------|----------------|-----------------|--------------------|-----------------|----------|
| 3 | 2.09% | 50 | - | - | 50 | - | |
| 5 | 3.85% | 50 | - | - | - | 50 | |
| 2 | 4.36% | - | 50 | - | 50 | - | |
| 1 | 8.30% | - | - | 50 | 50 | - | Brown |
| 4 | 15.35% | - | - | 50 | - | 50 | Brown |
| 6 | 19.27% | - | 50 | - | - | 50 | |
| 7 | | 10 | - | - | 90 | - | |
| 8 | | 90 | - | - | 10 | - | |
| 9 | | - | 10 | - | 90 | - | |
| 10 | | - | 90 | - | 10 | - | |
| 11 | | - | - | 10 | 90 | - | Brown |
| 12 | | - | - | 90 | 10 | - | Brown |

Fig. 1